

PERFORMANCE GRADE HOT MELT PACKAGING TAPE



TYPICAL APPLICATIONS

- For critical closure manual or automated industrial carton sealing of medium-weight cartons that are subjected to increased handling stress

PRODUCT FEATURES

- Instant, permanent bond to a wide range of substrates and surfaces
- Special release coating for consistent, low force unwind off the roll
- Offers Good to the Core® performance that enhances production while reducing tape waste
- Engineered with a high-tack adhesive and Hold Strong® technology to keep carton seals intact

CONSTRUCTION

Overall Grade/Function: Performance
Backing: 35 micron biaxially oriented polypropylene cast film
Adhesive: Synthetic rubber/resin hot melt

STANDARD WIDTH(S)

48 mm 53 mm 72 mm

STANDARD LENGTH(S)

50 m 100 m 914 m 1371 m

Contact your Shurtape sales representative for other available sizes

APPLICABLE STANDARDS

ASTM D1974/D1974M-16; CID A-A-1684C; FDA Indirect Contact CFR 21, 175.105; FDA Indirect Contact CFR 21, 177.1520

STORAGE AND USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

COLOR(S)



CLEAR
(CLR)



TAN
(TAN)

PHYSICAL PROPERTIES STANDARD METRIC

Thickness	2.2 mils	0.056 mm
Tensile Strength (Longitudinal)	30 lbs/in width	52.5 N/10 mm
Tensile Strength (Transverse)	55 lbs/in width	96.3 N/10 mm
Elongation	150%	150%
Adhesion to Stainless Steel	50 oz/in width	5.47 N/10 mm
Adhesion to Backing	5 oz/in width	0.55 N/10 mm
Holding Power to Fiberboard	25,000+ minutes	25,000+ minutes
Application Temperature Range	35 F to 110 F	2 C to 43 C
Service Temperature Range	-20 F to 150 F	-29 C to 66 C

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

