

HP 200®

Shurtape®
TRUE TO YOUR WORK™

PRODUCTION GRADE HOT MELT PACKAGING TAPE

TYPICAL APPLICATIONS

- For manual or automated industrial carton sealing of medium-weight cartons in normal manufacturing and shipping environments

PRODUCT FEATURES

- Instant, permanent bond to a wide range of substrates and surfaces
- Special release coating for consistent, low force unwind off the roll
- Offers Good to the Core® performance that enhances production while reducing tape waste
- Engineered with a high-tack adhesive and Hold Strong® technology to keep carton seals intact

CONSTRUCTION

Overall Grade/Function: Production

Backing: 30 micron biaxially oriented polypropylene cast film

Adhesive: Synthetic rubber/resin hot melt

STANDARD WIDTH(S)

36 mm 48 mm 53 mm 72 mm

STANDARD LENGTH(S)

50 m 100 m 914 m 1371 m 1828 m

Contact your Shurtape sales representative for other available sizes

STANDARD CORE SIZE

3 in

APPLICABLE STANDARDS

ASTM D1974/D1974M-16; CID A-A-1684C; FDA Indirect Contact CFR 21, 175.105

STORAGE AND USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

COLOR(S)



PHYSICAL PROPERTIES

	STANDARD	METRIC
Hand Roll (HR) Thickness	1.8 mils	0.046 mm
Machine Roll (MR) Thickness	1.9 mils	0.048 mm
Tensile Strength (Longitudinal)	27 lbs/in width	47.3 N/10 mm
Tensile Strength (Transverse)	44 lbs/in width	77.1 N/10 mm
Elongation	150%	150%
Adhesion to Stainless Steel	44 oz/in width	4.82 N/10 mm
Adhesion to Backing (Hand Rolls)	18 oz/in width	1.97 N/10 mm
Adhesion to Backing (Machine Rolls)	4 oz/in width	0.44 N/10 mm
Holding Power to Fiberboard	15,000+ minutes	15,000+ minutes
Application Temperature Range	35 F to 110 F	2 C to 43 C
Service Temperature Range	-20 F to 150 F	-29 C to 66 C

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.



Shurtape Technologies, LLC | PO BOX 1530 Hickory, NC 28603-1530 USA | Phone 1.888.442.TAPE (8273) | Fax 800.335.7651 | shurtape.com

ISO 9001 CERTIFIED QUALITY SYSTEM

Shurtape® is a registered trademark of Shurtape Technologies, LLC Form# MMC 00599-TDS-HP-200-03/16/2023